



APPLICATIONS

MEDITE PREMIER FR Euroclass B panel products are suitable for use as wall linings, partitions, display panels, ceilings etc. Typical installations are: hotel foyers, offices, public libraries, schools, court houses, hospitals and cinemas. MEDITE PREMIER FR products are not suitable for external or structural applications, or where exposure to water or high relative humidity may be encountered. MEDITE PREMIER FR Euroclass B is suitable for use in internal dry conditions as defined in EN622 part 5. Boards of this type are suitable for use in Hazard Class 1 of EN 335-3.

PERFORMANCE-FIRE RESISTANCE

MEDITE PREMIER FR Euroclass B panels applied as the wall skin in a symmetrical non-load bearing partition were tested in accordance with the criteria of BS 476: Part 22: 1987. The partition specification as detailed in the technical user guide has to be fully duplicated in order to achieve a fire resistance performance of 60 minutes for Euroclass B panels. Please refer to the technical user guideline "MEDITE PREMIER FR 60 minute Partition Wall" which can be downloaded from the MEDITE PREMIER FR Product page of our website.

APPEARANCE

MEDITE PREMIER FR Euroclass B is distinguishable from other MDF products by their pink identification colour.

MACHINING/FINISHING

Cut or profiled edges of MEDITE PREMIER FR Euroclass B products should first be sanded to a suitable grit finish, prior to painting. When choosing a coating system it should be confirmed with the paint manufacturer that the coating will not adversely affect the classification of the MEDITE PREMIER FR panel. There is a variety of flame retardant paints which provide the same finish and wear qualities equal to general decorative paints. The method of application will depend directly on the type of paint selected.

CONDITIONING

The moisture content of MEDITE PREMIER FR is in the range of 5 - 9% at the time of manufacture. Changes in dimensions of wood and wood-based sheet materials occur due to changes in relative humidity. For this reason, MEDITE PREMIER FR panels should be conditioned to the final environment for two to three days before cutting and fixing.





AUTHORITY

MEDITE PREMIER FR Euroclass B (EN 13823 and EN 11925-2) is manufactured under an NSAI registered I.S. EN ISO 9001 quality management system.

SUPPLY

MEDITE PREMIER FR Euroclass B is produced in the following standard panel sizes:

CLASS B - 1220 x 2440 and 1220 x 3050mm in 6, 12, 15, 18 and 25mm thicknesses. Other sizes and thicknesses available on request subject to minimum order quantities.

FIRE RATING

Certification available on request.

SERVICE

For further information and/or technical advice regarding processing and painting/finishing of MEDITE PREMIER FR, please contact MEDITE Technical Support Personnel:

UK: +44 (0) 1322 424900 Ireland: +353 5 181 0205 Germany: +49 32221097221 France: +33 975189830

Netherlands: +31 858886230 Belgium: +32 28086256

All MEDITE MDF products supplied for use in the construction and civil engineering industries are CE marked according to the requirements of the harmonised European standard for wood based panels EN 13986. This provides the necessary assurance to customers and users that MEDITE conforms with the European MDF standard, EN 622-5 and meets all the essential requirements for the Construction Products Directive that are relevant to the product.

In accordance with the provisions of Third Party Certification required within the Final Regulations Order of the Airborne Toxic Control Measure (ATCM) by the California Air Resources Board (CARB) all MEDITE MDF products are CARB Phase 2 Compliant. The approved Third Party Certifier (TPC) Entwicklungsund Pruflabor Holztechnologie GmbH (EPH – TPC No W-08-010) is contracted by MEDITE to perform the quarterly assessment of the factory production control and to have the stipulated formaldehyde tests carried out by the accredited EPH test laboratory.

MEDITE PREMIER FR MDF TECHNICAL SPECIFICATION SHEET

PROPERTY	RANGE	TEST METHOD	UNITS	>4 to 6mm	>6 to <9mm	9 to 12mm	>12 to 19mm	>19 to 25mm
Internal Bond	Min	EN 319	N/mm²	0.65	0.65	0.45	0.45	0.45
Modulus of Rupture	Min	EN 310	N/mm²	23.0	23.0	20.0	18.0	15.0
Modulus of Elasticity	Min	EN 310	N/mm²	2,700	2,700	1,700	1,600	1,500
Screw Holding Face	Min	EN 320	N	-	-	-	1000	1000
Screw Holding Edge	Min	EN 320	N	-	-	-	600	600
Moisture Content	Min-Max	EN 322	%	5.0-9.0	5.0-9.0	5.0-9.0	5.0-9.0	5.0-9.0
Thickness Tolerance	Min-Max	EN 324-1	mm	+/-0.15	+/-0.15	+/-0.15	+/-0.15	+/-0.15
Thickness Swelling (24hrs)	Max	EN 317	%	30.0	17.0	16.0	14.0	12.0
DIMENSIONAL MOVEMENT								
Length/Width	Max	EN 318	%	0.40	0.40	0.40	0.30	0.25
Thickness	Max	EN 318	%	6.0	6.0	5.0	4.0	4.0

For information regarding availability of other MEDITE products, please contact MEDITE EUROPE DAC sales personnel. The results as listed above are the minimum specification requirements for all flame retardant Medium Density Fibreboard manufactured by MEDITE EUROPE DAC. All board parameters are in compliance with EN 622 parts 1 & 5. As part of the MEDITE EUROPE DAC product development programme, the right to modify product specifications without notice is reserved. MEDITE PREMIER FR conforms to E1 formaldehyde levels as well as also complying with the lower levels required by CARB phase 2.

This leaflet is provided for information purposes only and no liability or responsibility of any kind is accepted by MEDITE EUROPE DAC or their representatives. MEDITE EUROPE DAC have used reasonable efforts to verify the accuracy of any advice, recommendation or information. MEDITE EUROPE DAC reserves the right to alteration of its products, production information and range without notice. As we continually update our technical datasheets please check on **www.mdfosb.com** to ensure you have the latest version.





V 06/21

